

General description

TECBOND 803-PL is a peelable adhesive for credit card attachment, magazine tip ins, removable labels, promotional items give always bonded to most packaging.

The Tecbond 803-PL is ideally suited to applications which are cost sensitive and where some staining of the substrates is acceptable.

Formulated for clean machine running with low char and low stringing characteristics.

Technical characteristics

Adhesive type:	Synthetic Polymer Based Hotmelt
Colour:	Clear
Molten tack:	Medium
Brookfield viscosity (ASTM D3236)	1700 cps @ 180°C / 356°F (typical value)
Suggested application temperature:	150-170°C / 302-338°F
Ring & Ball softening point (ASTM E28)	111°C / 232 (typical value)
Heat Resistance BS5340	75°C / 167°F
Open Time:	Medium

Methods of application

Bulk hotmelt tank, Spray and jet application

Suggested application temperature

Suggested application temperature is 150-170°C / 302-338°F depending on substrates to be bonded.

Packaging

Physical form:	Small pillows
Carton weight:	15kg / 33lb Carton
Pallet weight:	750 kg / 1650lb

F.D.A approved. All the constituent parts of this adhesive have been approved by the American F.D.A under C.F.R 21.175.105 (Adhesives).

Health & safety

Please refer to Power Adhesives Safety Data Sheet

The information contained on this data sheet is for guidance only. It is the result of careful laboratory evaluations by trained and qualified staff using British Standard or similar test methods. However, no warranty is expressed or implied regarding the accuracy of this data or the suitability of the adhesive for any specific purpose. In every case we strongly recommend that the user shall make their own tests to determine to their own satisfaction the suitability of the adhesive for their particular purpose. Neither seller nor manufacturer shall be liable for any injury, loss, damage. Direct or consequential arising out of the use or inability to use the product.

Health & Safety

Hotmelt adhesives pose virtually no hazards to health when used in normal industrial practice, but because they are used in a molten state at high temperatures there is a risk of thermal burns. Skin contact with molten hotmelt should be avoided and precautions taken against accidental splashes of adhesive. The use of overalls, cotton gloves and safety glasses help minimise the risk of burns.

Inhalation: Vapours given off during normal operation are not considered toxic, but if overheated, chemical breakdown of the components may occur releasing a complex mixture of organic materials, some of which may be toxic or irritant. Ensure hotmelts are run at the recommended operating temperatures and use in a well-ventilated area.

Eye contact: For solid hotmelt treat as inert particles and irrigate copiously with clean fresh water. For molten hotmelt irrigate with cold water and seek medical advice immediately.

Skin contact: Solid cold hotmelt is harmless to the skin. Wash hands with soap and water. Skin affected by molten hotmelt should be plunged into cold water immediately and left until the burning sensation subsides. If no tap is accessible have a bucket of clean cold water available. If coated with hotmelt move fingers to prevent a tourniquet effect as it cools. Do not remove the adhesive when molten as it might remove skin to quite a depth leaving a raw wound. Even when solid remove with care as the above may still occur. If difficult to remove, with medical approval, olive oil or liquid paraffin should be soaked into a cotton wool pad and placed over the affected area. This will slowly soften the adhesive into the pad. When hotmelt is removed treat as a normal burn.

Fire: Not normally a hazard, but in a fire hotmelts are combustible, use dry powder or CO2 extinguisher. Do not use water.

Storage Store in a clean dry place at temperatures between 41°F and 86°F with boxes closed. Do not expose to direct sunlight or localised heat sources such as radiators or hot pipes.

Equipment purging Machine purging is not normally required when changing adhesives within the same chemical type. However it is recommended that the equipment is purged when changing from one type to another. Mixing an EVA based adhesive with a Metallocene based Adhesive will block filters and nozzles.

Removal of glue Assembled components can be separated by heating assembly to a temperature slightly above the heat resistance figure.

Eva & polypropylene: Residues of EVA and polypropylene based hotmelts can be removed from components with white spirit.

Polyamide: Residues of Polyamide based hotmelt can be removed from components with acetone.

Please note The information contained on this data sheet is for guidance only. It is the result of careful laboratory evaluations by trained and qualified staff using British Standard or similar test methods. However, no warranty is expressed or implied regarding the accuracy of the data or the suitability of the adhesive for any specific purpose. In every case, we strongly recommend that the user shall make their own test to determine to their own satisfaction the suitability of the adhesive for their particular purpose. Neither seller nor manufacturer shall be liable for any injury, loss, damage, direct or consequential arising out of the use or inability to use the product. Further information is always available to help solve your adhesive problems. Should you require any further information on our adhesives or applicators please contact your nearest distributor.